

Construction

Technical Data Sheet

Acronal® NX 4623



Chemical Nature

Aqueous acrylate copolymer dispersion for mortar modification

Properties

Typical Properties

Solids content	%	~ 47.0
pH		~ 10.0
Viscosity at 23 °C (Brookfield RV, Spindle #4, at 50 rpm)	mPa s	~ 100 – 1200

Other properties of the dispersion

Density	lbs/gal	ca. 8.71
Dispersion type		Anionic
Stability in mortar/cement		Excellent
Freeze-Thaw Stability (tested at 15% solids, 1 cycle; freeze at 10 °F 16 hrs, thaw 8 hrs)		Good

Properties of the film

Appearance		Translucent
Surface		Non-tacky
Glass transition temperature T _g (DSC)	°C	ca. 12
Mechanical strength*		
Tensile strength	psi	ca. 925
Elongation at break	%	ca. 400

*This data is to be used for comparative purposes.

Applications

Features

Acronal® NX 4623 is recommended for use in mortar patching or spraying applications. Admixture compositions formulated with Acronal 4623 show excellent high temperature open time stability with many types of cement, entrain low air, and provide excellent freeze/thaw stability. Acronal 4623 is also recommended for use in cementitious ceramic tile thin-set adhesives, modification of mortars and cement repair systems. Mortar compositions modified with Acronal 4623 exhibit better flexural, tensile strengths and show increased resistance to water permeability relative to unmodified mortar compositions.

Processing

Acronal® NX 4623 already contains an anti-foam for use in combination with hydraulic binders. If additional antifoam is required, it is advisable to carry out trials with 0.3 - 1% Lumiten® E-L, or similar defoamers.

In order to achieve adequate stability on prolonged storage, it is advisable to add a small proportion of a suitable preservative to the products produced with Acronal® NX 4623. The suitability of the preservative must be determined by trials and checked at regular intervals.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Material Safety Data Sheet

All safety information is provided in the Material Safety Data Sheet Acronal® NX 4623.

Storage

Acronal® NX 4623 has a shelf life of six months from delivery date, provided it is stored in accordance with the "Handling and Storage of polymer dispersions" brochure. Technical information regarding the storage of BASF polymer dispersion products is available upon request.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Acronal is a registered trademark of BASF Group.

© BASF Corporation, 2015



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Pigments
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: edtech_info@basf.com
www.basf.us/dpsolutions