

# Industrial Coatings

## Technical Data Sheet

# Basonat<sup>®</sup> HI 290 B



<b>Product Description</b>	Basonat <sup>®</sup> HI 290 B is an aliphatic polyisocyanate for lightfast and weather-resistant two-pack polyurethane coatings. It is an approximately 90% solids solution in n-butyl acetate.
<b>Key Features &amp; Benefits</b>	<ul style="list-style-type: none"><li>- Excellent weather and chemical resistance</li><li>- Excellent physical properties</li><li>- Non yellowing</li></ul>
<b>Chemical Composition</b>	Polyisocyanate based on isocyanurate-modified hexamethylene diisocyanate (HDI)

### Properties

<b>Typical Characteristics</b>	Appearance	liquid
	Non-volatile	89 – 91%
	Viscosity at 23°C	400 – 600 cps
	Shear rate D	1,000 s <sup>-1</sup>
	Hazen color number	≤ 60
	Density at 20°C	1.13 g/cm <sup>3</sup> , 9.43 lbs/gal
	NCO content	19.3 – 20.3%
	NCO equivalent weight (as supplied)	~ 212

**Crosslinking** Used to crosslink most hydroxy-containing resins such as Joncryl<sup>®</sup> acrylics and hydroxy functional polyesters.

**Diluent tolerance** Can be diluted with esters, ketones, glycolether acetates or with aromatic hydrocarbons. Only urethane-grade solvents should be used to lessen the possibility of reacting with water.

If diluted to a polyisocyanate fraction of less than 40%, turbidity, flocculation, and/or sedimentation may occur during storage. Storage trials should always be conducted.

These typical values should not be interpreted as specifications.

The NCO equivalent weight indicates the amount of Basonat<sup>®</sup> polyisocyanate as supplied containing 1 Mol of active NCO.

### Applications

Basonat<sup>®</sup> HI 290 B is used to formulate lightfast and weather-resistant coatings.

Results from long-term weathering tests show that in most cases gloss retention is better using isocyanurates than with biurets of hexamethylene diisocyanates (Basonat<sup>®</sup> HB grades).

Basonat<sup>®</sup> HI 290 B is recommended for applications such as:

- Interior/exterior general industrial metal coating applications
- Interior/exterior plastic component coating applications
- Interior/exterior wood coatings for floor, furniture, or millwork applications
- Interior/exterior Automotive OEM or refinish applications

**Processing**

The theoretical equivalent amount of polyisocyanate required for crosslinking is computed using the formula below:

$$\frac{0.075 \times [\text{OH number}] \times [\% \text{ non-volatile fraction of OH component}]}{[\% \text{ NCO}]}$$

**Example**

Basonat<sup>®</sup> HI 290 B and Joncryl<sup>®</sup> 922

Joncryl<sup>®</sup> 922

OH number	140 mg KOH/g polyol on solids
Non-volatile fraction, Nv	80%
NCO content (Basonat <sup>®</sup> HI 290 B)	19.8%

$$\frac{0.075 \times 140 \times 80}{19.8} = 42.4$$

Basonat<sup>®</sup> HI 290 B dosage rate for 100g Joncryl<sup>®</sup> 922 as supplied = 42.4g.

Solvents, pigments, or extenders, etc. used should be free from compounds containing active hydrogen groups such as water, alcohols, or amines.

A water content of less than 500 ppm in solvents and binders in two-component polyurethane coatings is acceptable.

---

**Safety**

**General**

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

**Material Safety Data Sheet**

All safety information is provided in the Material Safety Data Sheet for Basonat<sup>®</sup> HI 290 B.

---

## Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

*Basonat is a registered trademark of BASF Group.*

© BASF Corporation, 2010



**Responsible Care®**  
*Good Chemistry at Work*

BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® goto:

U.S.: [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)

Canada: [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)

México: [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

### **U.S. & Canada**

BASF Corporation  
1609 Biddle Avenue  
Wyandotte, Michigan 48192  
Phone: (800) 231 – 7868  
Fax: (800) 392-7429  
Email: [polyorders@basf.com](mailto:polyorders@basf.com)  
Email: [edtech\\_info@basf.com](mailto:edtech_info@basf.com)  
[www.basf.com](http://www.basf.com)

### **Mexico**

BASF Mexicana, S.A. de C.V.  
Av. Insurgentes Sur # 975  
Col. Ciudad de los Deportes  
C.P. 03710  
Mexico, D.F.  
Phone: (52-55) 53-25-27-87  
(52-55) 53-25-26-87  
Fax: (52-55) 56-11-48-97