

Adhesives

Technical Data Sheet

Butofan[®] NS 166



Aqueous polymer dispersion used to manufacture pressure-sensitive adhesives for self-adhesive products

Chemical Nature

Aqueous dispersion of a styrene/butadiene copolymer containing carboxyl groups

Properties

Typical Properties

Solids content	%	~ 51.0 ± 1.0
pH		~ 8.8
Viscosity (Brookfield RV, Spindle #2, at 20 rpm)	mPa s	~ 250 – 700

Other properties of the dispersion

Density	lbs/gal g/cm ³	ca. 8.3 ca. 1.0
Average particle size	μm	ca. 0.18
Bound Styrene	%	ca. 35
Dispersion type		anionic
Antioxidant		non-staining

Properties of the film

Density	g/cm ³	ca. 0.98
Glass transition temperature (DSC)	°C	ca. -40
Mechanical strength *		
Tensile strength	lbs/in ²	80
Elongation at break	%	1200
Appearance		clear, transparent
Surface		tacky
Flexibility		high

*These figures should be taken for comparison purposes only. All that can be obtained from them is an idea of the order of magnitude concerned.

Compatible with

Polymer dispersions

Butofan[®] NS 144, 208, 222, some Acronal[®] anionic dispersions. Compatibility must be tested in each case.

Thickeners

Collacral[®] VAL, Latekoll[®] MD na

Resins

Commercial rosin, rosin ester and hydrocarbon tackifier dispersions. Compatibility must be tested in each case.

Application

Field of application

General purpose adhesives requiring high specific adhesion to a variety of substrates. Manufacture of pressure-sensitive adhesives for self-adhesive products. This is often done in combination with tackifier resins. Figure 1 summarizes a lab study in which several commercially available tackifier dispersions were blended with Butofan[®] NS 166 and tested for pressure sensitive performance.

Processing

Butofan® NS 166 exhibits good chemical and mechanical stability. Adhesives based on Butofan® NS 166 can be processed using standard latex compounding and applied by conventional coating methods such as Meyer bar, reverse roll, reverse gravure and slot die.

The addition of about 0.5% wetting agent (e.g. Lumiten® I-SC or Pluronic® L-92) can help if problems of poor substrate wettability arise. Commercial defoamers can be used (e.g. Drew Plus® L-108) up to approximately 0.2% on the adhesive.

It is recommended that a preservative be added to adhesives containing Butofan® NS 166 to protect from microbial attack. Selection and suitability of such additives must be verified by trials. Recommendations available.

As with other styrene/butadiene latex based adhesives, those based on Butofan® NS 166 can contribute to staining of pressure-sensitive paper labels articles after a period of time. In general, this effect can be reduced by priming of the substrate with suitable primers selected, verified and monitored by trials.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Material Safety Data Sheet

All safety information is provided in the Material Safety Data Sheet for Butofan® NS 166.

Storage

Butofan® NS 166 has a shelf life of six months from delivery date, provided it is stored in accordance with the "Handling and Storage of polymer dispersions" brochure. Technical information regarding the storage of BASF polymer dispersion products is available upon request.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Butofan is a registered trademark of BASF Group.

© BASF Corporation, 2015



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Pigments
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: edtech_info@basf.com
www.basf.us/dpsolutions