

Formulation Additives

Technical Data Sheet

Foamaster[®] MO 2192 (old: Foamaster[®] VL)



Product Description Foamaster[®] MO 2192 is a defoamer recommended for SBR, NBR, PVC, PVAc, acrylic and other latex systems.

Chemical Composition Defoamer

Properties

Product Specifications

Density at 20 °C (DIN 51757)	0.92 – 0.96 g/cm ³
Viscosity at 20 °C (Brookfield)	150 – 300 mPa·s

Typical Characteristics

Appearance	cloudy, amber liquid
Ionic character	non-ionic
Water solubility	emulsifiable

These typical values should not be interpreted as specifications.

Applications

As a latex stripping defoamer, Foamaster[®] MO 2192 has proved to be very effective in latex polymerized with a variety of emulsifiers including rosin acid soaps, fatty acid soaps, alkyl sulfates and alkyl aryl sulfonates.

It effectively controls foaming in the flash tank during degassing, and in the stripping column. Liquid in nature and 100% active, this defoamer is readily dispersible in water and is recommended for SBR, NBR, PVC, PVAc, acrylic and other latex systems.

Dosage Foamaster[®] MO 2192 offers an easy handling do to the fact that it can be used as received, or as dispersion in water.

Dosage levels vary depending on the type and concentration of surfactants in the system, but Foamaster[®] MO 2192 used at 0.2 - 0.5%, calculated on solid content, has been found very effective.

Safety

General The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

Material Safety Data Sheet All safety information is provided in the Material Safety Data Sheet for Foamaster[®] MO 2192.

Storage

Foamaster® MO 2192 is subject to appropriate storage under the usual storage and temperature conditions, our products are durable for at least 1 year. Foamaster® MO 2192 should ideally be stored at temperatures between 2 and 27 °C. If the product was subject to temperatures below 0 °C, do not apply direct heat but allow warming to room temperature and mixing thoroughly before use.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Foamaster is a registered trademark of BASF Group.

© BASF Corporation, 2013



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Pigments
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: edtech_info@basf.com
www.basf.us/dpsolutions