

# Industrial Coatings

## Technical Data Sheet

# Joncryl<sup>®</sup> 1919



<b>Product Description</b>	Joncryl <sup>®</sup> 1919 is a block-resistant acrylic emulsion for hardboard primer coatings.
<b>Key Features &amp; Benefits</b>	<ul style="list-style-type: none"><li>- <b>Block resistance</b></li><li>- <b>Excellent water resistance</b></li><li>- <b>Excellent adhesion</b></li><li>- <b>Low VOC</b></li></ul>
<b>Chemical Composition</b>	Acrylic emulsion

### Properties

<b>Typical Properties</b>	Appearance	semi-translucent emulsion
	Non-volatile at 145°C (2g, 30 minutes)	47%
	pH at 25 ± 1°C	8.0
	Viscosity at 25.0 ± 0.2°C (Brookfield #3LV, 30 rpm, 30 seconds)	1600 cps
	Density at 20°C	1.04 g/cm <sup>3</sup> (8.70 lbs/gal)
	MFFT	19°C
	Tg	29°C
	Freeze-thaw stable	No

These typical values should not be interpreted as specifications.

### Applications

Joncryl<sup>®</sup> 1919 is a unique acrylic emulsion that exhibits low minimum film forming temperature, yet offers excellent block and water resistance. Joncryl<sup>®</sup> 1919 is ideally suited for high PVC primers used over hardboard and cement fiberboard substrates.

Joncryl<sup>®</sup> 1919 is recommended for applications such as:

- Interior/exterior primers on wood, hardboard, cement fiberboard, and composite wood applications

### Formulation Guidelines

**Solvent Levels** - Normal primer cure temperatures range from 180 – 250°F maximum board surface temperature. This is generally enough heat to obtain a good performing film, even at PVC's in excess of 55. The addition of low levels of ethylene glycol mono butyl ether, propylene glycol t-butyl ether or propylene glycol mono butyl ether may further enhance film formation. Caution should be taken not to include too much solvent, as this may encourage blistering or blocking of the coating.

## Performance Evaluation

Approximately two wet mils of coating was applied to medium density fiberboard. The panel was baked for 15 minutes at 300°F in a high velocity oven. The panel was then immediately placed in an IR oven until a board surface temperature (BST) of 250°F was reached. The panel was allowed to cool to a BST of 150°F before a face-to-face block test was performed. The panel was allowed to cool for a total of 15 minutes before a tape adhesion test was performed.

Block test at 250 psi	No blocking
Adhesion test	Little adhesion failure at coating/substrate interface; mostly substrate failure

## Starting Point Formulation

The following starting point formulation is recommended for an initial evaluation of Joncryl® 1919. Modification of the formulation may be required to achieve desired results for specific applications.

### Joncryl® 1919 HARDBOARD PRIMER, Formula 609-K

Materials	Pounds	Gallons
Joncryl® 1919	236.3	27.42
Water	48.8	5.86
FoamStar® SI 2292 NC	4.3	0.58
Dimethyl ethanolamine (DMEA)	2.6	0.35
Ti-Pure <sup>1</sup> R-902	245.8	7.38
Atomite <sup>2</sup> Calcium carbonate	451.4	20.06
<b>Disperse to 5 Hegman</b>		
<b>Let-down:</b>		
Water	163.0	19.56
Joncryl® 1919	157.5	18.27
FoamStar® SI 2292 NC	2.2	0.29
Rheovis® PU 1250 NC	2.1	0.23
<b>Total</b>	<b>1,314.0</b>	<b>100.00</b>

### Formulation Attributes

Solids	67.3% by wt, 48.2% by volume
Viscosity	50 cps
PVC	57.0%
VOC (calculated)	21 g/l, 0.17 lbs/gal

<sup>1</sup>Trademark of The Chemours Company.

<sup>2</sup>Registered trademark of ECC America Inc. Corporation.

## Safety

### General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

### Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl® 1919.

## Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

*FoamStar, Joncryl, and Rheovis are registered trademarks of BASF Group.*

© BASF Corporation, 2016



**Responsible Care®**  
*Good Chemistry at Work*

BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)

Canada: [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)

México: [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

**U.S & Canada**

BASF Corporation  
24600 W Eleven Mile Road  
Southfield, MI 48034  
ph: 1(800) 231-7868  
fax:1(800) 392-7429  
Email: [Custserv\\_charlotte@basf.com](mailto:Custserv_charlotte@basf.com)  
Email: [edtech\\_info@basf.com](mailto:edtech_info@basf.com)  
[www.basf.us/dpsolutions](http://www.basf.us/dpsolutions)

**Mexico**

BASF Mexicana, S.A. de C.V.  
Av. Insurgentes Sur # 975  
Col. Ciudad de los Deportes  
C.P. 03710  
Mexico, D.F.  
Phone: (52-55) 5325-2756  
Fax: (52-55) 5723-3011