

Industrial Coatings

Technical Data Sheet

Joncryl[®] 550 Polyol



Product Description	Joncryl [®] 550 is a conventional solids, acrylic polyol for polyurethane coatings.
Key Features & Benefits	<ul style="list-style-type: none">- Lacquer-like dry times- Excellent gloss and gloss retention- Good chemical resistance
Chemical Composition	Acrylic polyol

Properties

Typical Properties

Appearance	clear liquid
Hydroxyl number	~ 96
Non-volatile at 150°C (0.5g, 60 minutes)	~ 63.0%
Viscosity at 25.0°C ± 0.5°C (Brookfield #4LV, 30 rpm, 30 seconds)	~ 9,500 cps
Density at 20°C (68°F)	1.05 g/cm ³ (8.85 lbs/gal)
Equivalent weight as supplied, of solids	1,000, 620
Tg (measured)	49°C (120.2°F)
Solvent	PM-acetate/toluene
Freeze-thaw stable	Yes

These typical values should not be interpreted as specifications.

Applications

Joncryl[®] 550 is a solvent variation of a hydroxyl-functional acrylic oligomer designed for conventional solids isocyanate crosslinked systems. Joncryl[®] 550 is a drop-in replacement with minimum levels of reformulation and testing for several commercially available competitive acrylic polymers. It is a typical “workhorse” acrylic resin supplied in a 65/35 blend of PM-acetate/toluene. Joncryl[®] 550 differs from Joncryl[®] 587 in cure time (faster) and UV durability.

Joncryl[®] 550 is recommended for applications such as:

- Interior/exterior automotive OEM and refinish applications
- Interior/exterior general metal industrial coating applications
- Interior/exterior plastic component coating applications
- Interior/exterior concrete coatings

Joncryl[®] 550 is available in the following solvents as the applicable product name:

- Xylene as Joncryl[®] 551
- n-Butyl Acetate as Joncryl[®] 552
- t-Butyl Acetate exempt solvent as Joncryl[®] 558

Please refer to each product’s Technical Data Sheet for performance information and specific starting point formulations.

SGO Polymerization Process

Joncryl® 550 is produced by the exclusive SGO (Solid Grade Oligomer) polymerization process. The SGO process does not utilize a reflux solvent, as does the conventional bulk polymerization process. When a polyol is made via conventional polymerization utilizing a different reflux solvent, a different molecular structure results. Efforts are made to make both versions of the product as close as possible, however, differences are unavoidable. Since the SGO process does not utilize a reflux solvent in its polymerization process, the resulting product is EXACTLY the same regardless of the solvent in which the resin is supplied.

The SGO process is a very high temperature and high-pressure process. When monomers enter this high temperature/pressure environment they become chemically excited and react in the same manner from batch-to-batch, minimizing quality issues.

Due to Joncryl® 550 being produced by the SGO process, it exhibits excellent clarity and significantly less objectionable residual monomer odor and is inherently low in color.

Formulation Guidelines

Crosslinker Selection – For maximum gloss retention properties, aliphatic isocyanates are recommended. The Trimer or Biuret versions of hexamethylene diisocyanate can be used. The Trimer version may give better gloss retention and reactivity. A ratio of 1.05:1 of isocyanate to hydroxyl is normally recommended in the industry. However, a ratio of 1:1 of isocyanate to hydroxyl is more economical and does not sacrifice performance properties.

Solvent Selection – Because the hydroxyl functionality of alcohols and glycol ethers can react with the isocyanate, their use should be avoided. Urethane-grade solvents should be used when available. Ketones will give the best viscosity/VOC due to a combination of good solvency and low density. Esters are the next best choice although they do not provide as low a viscosity/VOC as ketones due to their higher density. Generally, the lower the molecular weight of the solvent within the family, the lower the obtainable viscosity/VOC. Aromatics such as xylene and toluene provide good solvency and can be readily used in combination with the more polar solvents. Toluene especially provides low viscosity/VOC. Glycol ether acetates can be used, but normally do not provide low viscosity/VOC. PM-Acetate should be avoided due to its film retention characteristics. Exempt solvents have been found to work well and should be considered when lower VOC capability is desired.

Catalysis – Joncryl® 550 is normally catalyzed at 0.005% to 0.015% with dibutyltin dilaurate. Catalysis with 0.01% dibutyltin dilaurate on total binder solids is normally recommended. Higher catalyst levels will result in shorter pot lives and faster cure rates. 2,4-Pentanedione can be used to extend the pot life of systems when a tin catalyst has been utilized. Other catalysts such as zinc octoate and other metallic soaps can also be used.

Additives – BYK¹-320 is recommended at 2 pounds per 100 gallons of combined formulation in pigmented formulations. BYK¹-320 results in excellent flow and leveling as well as providing air release during manufacture and use. For applications where improved in-can clarity is desired, BYK¹-333, BYK¹-323, and other additives should be evaluated. Typical use levels of 0.5 – 2.0 pounds per 100 gallons are normally recommended. If a dispersant is necessary, Lecithin or Disparlon² KS-273N is recommended. For higher film build, thixotropes such as bentonite clays, fumed silicas, or organic additives such as Thixatrol³ can be used. CAB⁴-551-0.02 is recommended to modify flow properties when desired.

¹Registered trademark of BYK-Chemie GmbH.

²Registered trademark of King Industries, Inc.

³Registered trademark of Elementis Specialties, Inc.

⁴Registered trademark of Eastman Chemical Company.

Starting Point Formulation

The following starting point formulation is recommended for an initial evaluation of Joncryl® 550. Additional optimization of the formulation will be required to achieve desired results for specific applications.

Joncryl® 550 ACRYLIC URETHANE AUTO REFINISH CLEAR TOPCOAT, Formula 0382a155-2

Part A	Pounds	Gallons
Joncryl® 550	385.03	43.75
BYK ¹ -320	1.58	0.24
MAK	104.63	15.39
MIBK	104.63	15.69
MEK	103.33	15.40
Tinuvin® 1130	4.74	0.49
Tinuvin® 292	3.16	0.38
Irganox® 1010	3.16	0.33
1% DBTDL in 2,4-Pentanedione	3.16	0.39
Subtotal	713.42	92.06
Part B		
Basonat® HI 100	77.23	7.94
Total	790.65	100.00


Formulation Attributes

Solids	41.50% by wt, 33.00% by volume
Viscosity (Brookfield)	140 cps
NCO:OH ratio	1.05:1
VOC (calculated)	4.63 lbs/gal, 554.63 g/l

Viscosity/VOC Capability

The following graph illustrates the viscosity of a clear automotive topcoat formulation based on Joncryl® 550 as compared to a competitive acrylic polyol and Joncryl® 587.


Viscosity of Automotive Refinish Clears at 4.8 lbs/gal VOC



Cure/Dry Characteristics

The following graph illustrates the dry times/cure rates of a clear automotive topcoat formulation based on Joncryl® 550 as compared to a competitive product and Joncryl® 587.


Gardner Circular Hard Dry Time



Evaluation of Gardner Dry Times is very subjective. The graph represents a range of typical results.

Hardness Development

The following graph demonstrates the hardness development obtained with Joncryl® 550 as compared to a competitive product and Joncryl® 587.



Chemical Resistance

The following table compares the chemical resistance of clear coats based on Joncryl® 550 to a competitive product and Joncryl® 587. Test results are 24-hour covered spot tests.

	5% Sulfuric Acid	5% Hydrochloric Acid	5% Acetic Acid	5% Sodium Hydroxide	5% Ammonia	Xylene
Joncryl® 550	10	10	10	10	10	10
Competitive Product	10	10	10	10	10	10
Joncryl® 587	10	10	10	10	10	10

Note: 10 = No effect or recovers


Physical Properties

The following table contains physical properties for clear coats based on Joncryl® 550 as compared to a competitive product and Joncryl® 587.

	Gloss 20° / 60°	Pencil Hardness	Impact Direct / Reverse
Joncryl® 550	90 / 95	2H	160 / 80
Competitive Product	90 / 95	2H	100 / 50
Joncryl® 587	90 / 95	2H	30 / 10

QUV Weathering

The following graph demonstrates the accelerated weathering resistance obtained with Joncryl® 550 as compared to a competitive product and Joncryl® 587. Test conditions involve 4 hours of light at 50°C and UVB-313 bulbs followed by 4 hours of condensation at 40°C.



Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of personal protective equipment.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl® 550.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Basonat, Irganox, Joncryl and Tinuvin are registered trademarks of BASF Group.

© BASF Corporation, 2016



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® goto:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation
24710 W Eleven Mile Road
Southfield, MI 48033
ph: 1(800) 231-7868
fax: 1(800) 392-7429
Email: Custserv_charlotte@basf.com
Email: edtech_info@basf.com
www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.
Av. Insurgentes Sur # 975
Col. Ciudad de los Deportes
C.P. 03710
Mexico, D.F.
Phone: (52-55) 5325-2756
Fax: (52-55) 5723-3011