

Industrial Coatings

Technical Data Sheet

Laromer[®] PE 44 F



Product Description	Laromer [®] PE 44 F is a polyester- modified acrylic resin for the formulation of radiation-curable printing inks and coatings, for wood products, paper and plastics
Key Features & Benefits	<ul style="list-style-type: none">- <i>Minimal yellowing</i>- <i>Easy to blend with other photoinitiators</i>
Chemical Structure	Polyester acrylate

Properties

Typical Properties	Viscosity at 23 °C (73 °F) (ISO 3219 A) (Shear rate D 100 s ⁻¹)	~ 5.0 mPa s
	Acid value (EN ISO 3682)	≤ 5 mg KOH/g
	Iodine color number (DIN 6162)	≤ 10
	Density (ISO 2811-3)	~ 1.20 g/cm ³
	Flash point (DIN EN ISO 2719)	> 100 °C (212 °F)
	Physical form	low – medium viscous liquid
	Solubility, diluent tolerance	The Laromer [®] grades listed above are soluble in many solvents common to the coatings industry except in aliphatic hydrocarbons. For the formulation of low-viscous coatings they can be thinned with monomers such as Laromer [®] HDDA (hexanediol acrylate), Laromer [®] TMPTA (trimethylolpropane triacrylate) and Laromer [®] TPGDA (tripropylene glycol diacrylate) or with esters, ketones and aromatic hydrocarbons.
	Compatibility	The Laromer [®] grades can be homogenously mixed with most unsaturated acrylic resins such as other Laromer [®] grades.

These typical values should not be interpreted as specifications.

Applications

These resins have a balanced property profile are used as sole binders or in combination with other unsaturated acrylic resins for the formulation of electron-beam or UV curable printing inks or coatings. Laromer® PE 44 F is used in the following applications: coatings for wood, wood products, plastics, paper and printing inks.

Processing

All resins listed can be further diluted with low-volatile monomers such as monofunctional, difunctional or trifunctional acrylates. These are incorporated into the film during curing and thus influence its properties.

Monofunctional acrylates increase film flexibility. Difunctional acrylates have little influence on film hardness and flexibility while trifunctional acrylates increase film hardness.

With an adequate flash-off zone available, inert solvents may also be used. These must, however, be completely removed from the film prior to radiation curing.

A photo initiator must be added to allow curing by ultraviolet radiation. Suitable initiators are, among others, Irgacure® 819, Irgacure® TPO, Irgacure® TPO-L, Irgacure® 2100, Irgacure® 1173, Irgacure® 184, Irgacure® 500, and Irgacure® 127. Depending on the desired reactivity, the usual application rate is 2–5 %.

To increase the reactivity in thin films, a tertiary amine such as methyl diethanol amine or an amine synergist, such as an amino acrylate resin Laromer® PO 94 F or Laromer® PO 9103 can be added to formulations. Care must be taken to ensure that the amine does not react with the substrate, particularly pale-colored ones.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet Laromer® PE 44 F.

Storage

Laromer® PE 44 F must be protected from light and heat (below 30 °C [86 °F]) and kept in tightly sealed containers. Under these conditions, the shelf life is twelve months.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the ready make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF THE BASF TERMS AND CONDITIONS OF SALE.** Further, the descriptions, designs, data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the description, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Laromer and Irgacure are registered trademarks of BASF Group.

© BASF Corporation, 2015



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation
24710 W Eleven Mile Road
Southfield, MI 48033
ph: 1(800) 231-7868
fax:1(800) 392-7429
Email: Custserv_charlotte@basf.com
Email: edtech_info@basf.com
www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.
Av. Insurgentes Sur # 975
Col. Ciudad de los Deportes
C.P. 03710
Mexico, D.F.
Phone: (52-55) 5325-2756
Fax: (52-55) 5723-3011