Adhesives

Technical Data Sheet

Styronal[®] ND 430

Chemical Nature

Aqueous dispersion of a carboxylated styrene/butadiene copolymer used in the formulation of industrial adhesives for combining and laminating

D BASF

We create chemistry

	Properties		
Typical Properties	Solids content	%	~ 50.0
	pH value		~ 8.5
	Viscosity at 23 °C (Brookfield RV, Spindle #1, at	cps 20 rpm)	~ 100 – 350
Other properties of	Density	lbs/gal	ca. 8.3
the dispersion	Bound styrene	%	ca. 55
-	Residual Styrene	%	0.03 max
	Surface tension	nM/m	ca. 40
	Average Particle size	microns	ca. 0.25
	Dispersion type		anionic
Properties of the film	Glass transition temperature (DSC)	°C	-7
	Mechanical Strength*		
	Tensile strength	psi	ca. 1000
	Elongation at break	%	ca. 430
	Surface		slightly tacky
	* These values permit only a rou	igh comparison o	f film strengths
Compatible with			
Polymer dispersions	Butofan [®] NS 144, NS 166, NS 208, Acronal [®] NA 217, Acronal [®] 3422, Styrofan [®] ND 593		
Thickeners	Collacral [®] VL, Latekoll [®] D and casein solutions		
	Application		
	Styronal [®] ND 430 has outstanding mechanical and chemical stability. It displays excellent adhesion and serves as the base for foil to kraft wet laminating adhesives in conjunction with casein.		
Processing	We recommend adding a preservative to adhesives and coating materials that contain Styronal [®] ND 430 to protect them from microbial attack, particularly if their pH lies in the neutral range. The suitability of such additives must be verified and monitored in trials.		

	Safety
General	The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.
Material Safety Data Sheet	All safety information is provided in the Material Safety Data Sheet for Styronal® ND 430.
	Storage

Styronal[®] ND 430 has a shelf life of six months from delivery date, provided it is stored in accordance with the "Handling and Storage of polymer dispersions" brochure. Technical information regarding the storage of BASF polymer dispersion products is available upon request

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Styronal is a registered trademark of BASF Group.

© BASF Corporation, 2015



BASF Corporation is fully committed to the Responsible Care[®] initiative in the USA, Canada, and Mexico. For more information on Responsible Care[®] go to: U.S.: www.basf.us/responsiblecare_usa Canada: www.basf.us/responsiblecare_canada México: www.basf.us/responsiblecare_mexico

BASF Corporation Dispersions and Pigments 11501 Steele Creek Road Charlotte, North Carolina 28273 Phone: (800) 251 – 0612 Email: edtech_info@basf.com www.basf.us/dpsolutions