

Printing & Packaging Industrial Coatings

Technical Data Sheet

Tinuvin[®] 292 HP

BASF
We create chemistry

Product Description



Tinuvin[®] 292 HP is a liquid hindered amine light stabilizer especially developed for color sensitive coating applications.

Key Features & Benefits

- Versatile HALS with superior performance in both water- and solvent-based coatings
- Extends usable lifetime of coating by minimizing loss of gloss and cracking
- Excellent compatibility with a wide variety of coatings systems

Chemical Composition

Blend of Bis(1,2,2,6,6-pentamethyl-4-piperidyl) sebacate and Methyl 1,2,2,6,6-pentamethyl-4-piperidyl sebacate



Properties

Typical Properties

Appearance	colorless to slightly yellow liquid
CAS number	preparation
Molecular weight	mixture
Dynamic Viscosity at 20 °C	400 cps
Miscibility at 20 °C (g/100 g solution)	> 50% with most commonly used paint solvents < 0.01% with water

These typical values should not be interpreted as specifications.

Applications

Tinuvin® 292 HP is a very pure mixture of two active ingredients that help maintain this products' liquid state. It provides significantly extended lifetime to coatings by minimizing paint defects such as cracking and loss of gloss without adding additional color to the formulation.

Tinuvin® 292 HP is recommended for applications such as:

- Automotive coatings (non-acid catalyzed), especially refinish coatings
- Color sensitive durable industrial coatings
- Energy curable coatings (with no loss of cure speed)

Its high efficiency has been demonstrated in coatings based on a variety of binders such as:

- One- and two-component polyurethanes (water and solvent)
- Thermoplastic acrylics (physical drying)
- Thermosetting acrylics, alkyds and polyesters
- Alkyds (air drying)
- Waterborne acrylics
- Phenolics, vinylics
- Energy curable acrylics

Processing

The dispersion of Tinuvin® 292 HP in waterborne coatings may be facilitated by dilution with a water-miscible solvent such as butyl Carbitol¹.

The performance of Tinuvin® 292 HP can be significantly improved when used in combination with a UV absorber such as those recommended below. These synergistic combinations give coatings superior protection against gloss reduction, cracking, blistering, delamination and color change.

Light stabilizers may be added in two-coat automotive finishes to the base and clear coat. However, according to our experience the optimum protection is usually achieved by adding light stabilizers to the topcoat.

Possible interactions of Tinuvin® 292 HP with paint ingredients such as acid catalysts should be carefully evaluated.

Recommended concentration

The amount of Tinuvin® 292 HP required for optimum performance should be determined in trials covering a concentration range.

Clear coats & One-coat metallic shades:	0.5 – 2 % + 1 – 3 %	Tinuvin® 292 HP Tinuvin® 1130, Tinuvin® 384, Tinuvin® 928, or Tinuvin® 400
One-coat solid shades:	0.5 – 2 % alone or in combination with 1 – 3 %	Tinuvin® 292 HP Tinuvin® 1130, Tinuvin® 384, Tinuvin® 928, or Tinuvin® 400

(concentrations are based on weight percent binder solids)

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet Tinuvin® 292 HP.

Safety

Properly stored and protected, an unopened container of Tinuvin® 292 HP should have a shelf life of at least one year.

¹Trademark of The Dow Chemical Company.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Tinovin is a registered trademark of BASF Group.

© BASF Corporation, 2016



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation

24710 W Eleven Mile Road

Southfield, MI 48033

ph: 1(800) 231-7868

fax:1(800) 392-7429

Email: Custserv_charlotte@basf.com

Email: edtech_info@basf.com

www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.

Av. Insurgentes Sur # 975

Col. Ciudad de los Deportes

C.P. 03710

Mexico, D.F.

Phone: (52-55) 5325-2756

Fax: (52-55) 5723-3011