

Architectural Coatings

Preliminary Technical Data



We create chemistry

Acronal® PLUS 4240

Chemical Nature Acrylic latex resin.

Properties

Typical properties

Solids content, weight	%	~ 53.0
pH		~ 8.5
Viscosity (Brookfield)	cps	~ 500

Other properties of the dispersion

Specific gravity	lbs/gal	8.7
MFFT		7.0 °C
Particle size	nm	~ 240
Sensitivity to freezing	°C	Below 0

Applications

Fields of application

Acronal® PLUS 4240 is intended for use in exterior coatings.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Acronal® PLUS 4240.

Storage

Acronal® PLUS 4240 has a shelf life of six months from delivery date, provided it is stored in accordance with the "Handling and Storage of polymer dispersions" brochure. Technical information regarding the storage of BASF polymer dispersion products is available upon request.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Acronal is a registered trademark of BASF Group.

© BASF Corporation, 2016



BASF Corporation is fully committed to the Responsible Care® Initiative in the USA, Canada, and Mexico.
For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Resins
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: edtech_info@basf.com
www.basf.us/dpsolutions