

# Dispex<sup>®</sup> Ultra PA 4580

(old : Efka<sup>®</sup> 4580)



## general

high-molecular-weight dispersing agent

Dispex<sup>®</sup> Ultra PA 4580 stabilizes the pigment dispersion of inorganic and organic pigments and improves the following properties:

- strong viscosity reduction of pigment paste
- pigment loading
- gloss
- color strength
- flocculation stability
- anti-flooding behavior

Dispex<sup>®</sup> Ultra PA 4580 is compatible in a wide range of most commonly used water-based coatings. Its solubility is pH-independent, Dispex<sup>®</sup> Ultra PA 4580 does not have to be neutralized.

## chemical nature

acrylic polymer emulsion

## Properties

### physical form

clear, slightly yellowish liquid

### shelf life

Dispex<sup>®</sup> Ultra PA 4580 may partially solidify when stored below 10 °C (50 °F). Heat to 35–40 °C (95–104 °F) to reliquify. When kept in original unopened containers, it can be stored for up to 2 years from the date of manufacture.

### typical properties (no supply specification)

solvent	water
density at 20 °C (68 °F)	~ 1.05 g/cm <sup>3</sup>
active ingredients	~ 40 %
amine value	~ 19 mg KOH/g

## Application

Dispex<sup>®</sup> Ultra PA 4580 can be used exclusively as a dispersing agent or to formulate resin-free pigment concentrates for VOC-free applications.

### recommended concentrations

Calculation method for the required amount of active ingredient on pigment:

inorganic pigments	10 % of oil absorption value
organic pigments	25–50 % of BET value
carbon blacks	20 % of DBP absorption value

Dispex<sup>®</sup> Ultra PA 4580 should be incorporated in the mill base before adding the pigments.

**Safety**

When handling this product please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

**Note**

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

BASF SE  
Performance Additives  
67056 Ludwigshafen, Germany  
[www.basf.com/resins](http://www.basf.com/resins)  
[service-edc@basf.com](mailto:service-edc@basf.com)