

# Efka<sup>®</sup> PU 4009

(old : Efka<sup>®</sup> 4009)

## general

high-molecular-weight dispersing agent

Efka<sup>®</sup> PU 4009 is a polymeric dispersant for stabilizing inorganic and organic pigments. This results in:

- reduced dispersing time
- improved gloss
- prevention of flooding and floating problems
- higher color strength

Due to its particularly good combination of price and performance, Efka<sup>®</sup> PU 4009 is a very attractive substitute for conventional wetting and dispersing agents.

## chemical nature

modified polyurethane

## Properties

### physical form

clear, slightly yellowish liquid

### shelf life

Efka<sup>®</sup> PU 4009 may partially solidify when stored below 10 °C (50 °F). Heat to 35–40 °C (95–104 °F) to reliquify. When kept in original unopened containers, it can be stored for up to 4 years from the date of manufacture.

### typical properties (no supply specification)

solvent	butyl acetate/methoxypropyl acetate/2-butanol
density at 20 °C (68 °F)	~ 1.01 g/cm <sup>3</sup>
active ingredients	~ 60 %
flash point	24 °C (75°F)
acid value	~ 14 mg KOH/g
amine value	~ 12 mg KOH/g
color	≤ 5

## Application

Efka<sup>®</sup> PU 4009 was developed for use in universal solvent-based pigment concentrates, particularly where cost-effective performance is vital. It can also be used as a general dispersing agent for all solvent-based paints from high-performance industrial coatings to normal decorative paints.

**recommended concentrations**

Calculation method for the required amount of active ingredient on pigment:

inorganic pigments	10 % of oil absorption value
organic pigments	25–50 % of BET value
carbon blacks	20 % of DBP absorption value

Efka® PU 4009 should be incorporated in the mill base before adding the pigments.

**Safety**

When handling this product please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

**Note**

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted