

# FoamStar<sup>®</sup> ST 2400

## general

- member of a novel series of defoamers based on patented FoamStar<sup>®</sup> technology
- very fast bubble break versus conventional defoamers
- effective in industrial coatings based on acrylic emulsions
- good persistence

## chemical nature

defoamer based on patented FoamStar<sup>®</sup> technology and mineral oil

---

## Properties

### physical form

opaque, off-white liquid

### storage

FoamStar<sup>®</sup> ST 2400 should always be stored in tightly closed containers. Store in a cool place.  
If subjected to below freezing temperatures, FoamStar<sup>®</sup> ST 2400 may congeal or stratify. Warm to 122°F (50°C) and mix well before use.

### typical properties

dispersibility (10% in water)	non-dispersible
density	~ 7.2 lbs/gal
viscosity	~ 700 cps

---

## Application

FoamStar<sup>®</sup> ST 2400 will be equally effective in both the grind and the letdown.

- non-separating and non settling
- effective in industrial coatings based on acrylic emulsions
- very fast bubble break versus conventional defoamers
- effective against micro- and macro foam
- good persistence

### recommended concentrations

a dosage of 0.25 – 0.5% calculated on total formulation is recommended for effective defoaming.

## Contacts worldwide

## Asia

BASF East Asia Regional Headquarters Ltd  
45/F, Jardine House  
No. 1 Connaught Place  
Central Hong Kong  
China  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

## North America

BASF Corporation  
11501 Steele Creek Road  
Charlotte, NC 28273  
USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

## Europe

BASF SE  
Formulation Additives  
67056 Ludwigshafen  
Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

## South America

BASF S.A  
Rochaverá - Crystal Tower  
Av. das Nações Unidas, 14.171  
Morumbi - São Paulo-SP  
Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

**Validity**

This Technical Data Sheet is valid for all versions of the FoamStar ST 2400:  
FoamStar ST 2400, FoamStar ST 2400 NC.

**Safety**

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

**Note**

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

[www.basf.com/formulation-additives](http://www.basf.com/formulation-additives)