

North America

CAS # : Proprietary

CTFA Name: Proprietary

Physical Properties

Acid Value, mg KOH/g	4 Max.
Saponification Value, (mg KOH/g)	178 - 188
Iodine Value	1 Max.
Alpha Monoglyceride,%	22 - 25
Free Glycerine, %	1 Max.
Color, Gardner 1963	2.33 Max.
Water, %	0.5 Max.

Specifications and analytical methods are available upon request.

Typical Properties

Melting Point, °C	58 - 64
Appearance	White to off-white beads

Suggested Applications

Glycolube™ 38 is an external lubricant for PVC bottle, film and sheet components. Excellent processing/final product clarity – levels at 0.25-1.0 phr.

Manufacturing Location

This material is manufactured in Williamsport PA and has a shelf life of three (3) years from date of manufacturing.

For more information please contact your Arxada Account Manager or Distributor, or Arxada's Technical Sales Support at contact.allendale@arxada.com