

Transportation, Industrial, Furniture & Floor Coatings

Technical Data Sheet

Basonat® HI 100 NG



| | |
|------------------------------------|---|
| Product Description | Basonat® HI 100 NG is a solvent-free aliphatic polyisocyanate for lightfast and weather-resistant two-pack polyurethane coatings. |
| Key Features & Benefits | <ul style="list-style-type: none">- Excellent weather and chemical resistance- Excellent color stability in formulated automotive refinish clearcoat hardeners- Excellent hardness/flexibility for demanding applications |
| Chemical Composition | Polyisocyanate based on isocyanurate-modified hexamethylene diisocyanate (HDI) |

Properties

Typical Properties

| | |
|--|---|
| Appearance | clear liquid |
| Viscosity at 23°C, 1,000 s ⁻¹ | 2,500 – 4,000 cP |
| Hazen color number | ≤ 40 |
| Density at 20°C | ~ 1.17 g/cm ³ (9.76 lbs/gal) |
| NCO content | ~ 22% |
| NCO equivalent weight (as supplied) | ~ 191 |

These typical values should not be interpreted as specifications.

Applications

Basonat® HI 100 NG is used to formulate lightfast and weather-resistant coatings. Results from weathering tests show that in most cases, gloss retention is better using isocyanurates than with biurets of hexamethylene diisocyanates (Basonat® HB grades). Acrylic polyols should be used for maximum weather resistance.

Basonat® HI 100 NG is recommended for applications such as:

- Interior/exterior Automotive OEM or refinish applications
- Interior/exterior plastic component coating applications
- Interior/exterior general industrial metal coating applications
- Interior/exterior wood coatings for floor, furniture, or millwork applications

Diluent tolerance

Basonat® HI 100 NG is solvent-free and allows for a broad range of solvent choices in formulation, such as esters, ketones, glycol ether acetates, and aromatic hydrocarbons. Only “urethane grade” solvents should be used to lessen the possibility of reacting with water. Solvents with a water content of less than 500 ppm are acceptable. Pigments, extenders, etc. used should also generally be free from compounds containing active hydrogen groups such as water, alcohols, or amines.

If diluted to a polyisocyanate fraction of less than 40%, turbidity, flocculation, and/or sedimentation may occur during storage. Storage stability trials should always be conducted.

Crosslinking

Basonat® HI 100 NG can be used to crosslink most hydroxyl-functional resins such as Joncryl® acrylic polyols, Sovermol® solvent-free polyols, and hydroxyl-functional polyesters. The stoichiometric amount of Basonat® polyisocyanate can be calculated from the NCO equivalent weight (mass of polyisocyanate as supplied containing 1 mol of active NCO) and the hydroxyl equivalent weight of the polyol as follows:

$$\frac{\text{Mass of polyol as supplied}}{\text{Hydroxyl equivalent weight of polyol as supplied}} \times \text{NCO equivalent weight} = \text{Mass of polyisocyanate}$$

Alternatively, the stoichiometric amount of polyisocyanate required for crosslinking can also be calculated using the %NCO of the polyisocyanate, the nonvolatile content of the polyol, and the OH# of polyol solids as demonstrated below:

$$\frac{0.075 \times [\text{OH \# of polyol solids}] \times [\% \text{ nonvolatile content of polyol}]}{[\% \text{ NCO of polyisocyanate}]} = \text{Mass of polyisocyanate per 100g polyol}$$

Example

Basonat® HI 100 NG and Joncryl® RPD 950 AC/P

Joncryl® RPD 950 AC/P:

| | |
|----------------------------------|-------------------------------|
| OH number | 110 mg KOH/g on polyol solids |
| Nonvolatile content | 65% |
| NCO content (Basonat® HI 100 NG) | 22% |

$$\frac{0.075 \times 110 \times 65}{22} = 24.4 \text{ g Basonat® HI 100 NG per 100 g Joncryl® RPD 950 AC/P}$$

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Basonat® HI 100 NG.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Basonat, Joncryl, and Sovermol are registered trademarks of BASF Group.

© BASF Corporation, 2017



Responsible Care®
Good Chemistry at Work

BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation

24710 W Eleven Mile Road

Southfield, MI 48034

ph: 1(800) 231-7868

fax:1(800) 392-7429

Email: DispersionsPigmentsCC@basf.com

Email: edtech-info@basf.com

www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.

Av. Insurgentes Sur # 975

Col. Ciudad de los Deportes

C.P. 03710

Mexico, D.F.

Phone: (52-55) 5325-2756

Fax: (52-55) 5723-3011