

Industrial Coatings

Technical Data Sheet

Laromer® UA 8983 Aqua

(old: Laromer® LR 8983)



Product Description	Laromer® UA 8983 Aqua is a liquid aromatic polyurethane dispersion. It can be used in energy curable resin formulation for coating applications, such as wood, wood products, and plastic.
Key Features & Benefits	<ul style="list-style-type: none">- Excellent physical drying properties- Good resistance to household chemicals, and block- Good balance of hardness and flexibility- Suitable for 3-D objects
Chemical Composition	Water based aromatic urethane acrylate dispersion

Properties

Typical Properties	Appearance	clear, low viscous liquid
	Non volatile matter (DIN EN ISO 3251)	~ 42 %
	pH at 23°C (DIN ISO 976)	~ 8
	Viscosity at 23°C (DIN EN ISO 3219)	~ 300 cps
	Shear rate D	250 s ⁻¹
	Average particle size	~ 50 nm
	Density at 20°C (DIN EN ISO 2811)	~ 1.00 g/cm ³
	Minimum film forming temperature (DIN ISO 2115)	~ 0°C

These typical values should not be interpreted as specifications.

Applications

General Due to its good physical drying, formulations based on Laromer® UA 8983 Aqua are suitable for the coating of 3-D objects, where the full energy dose cannot be achieved during the UV curing process. These formulations lead to tack-free films with limited mechanical properties that are only obtained by UV curing.

Coating formulations based on Laromer® UA 8983 Aqua exhibit good resistance to household chemicals and block as well as provide a good balance between hardness and flexibility. The preferred methods of application are curtain coating and spraying. An economic feature of Laromer® LR 8983 is its ability to be recovered from the overspray of ultrafiltration.

Laromer® UA 8983 Aqua is recommended for applications such as:

- Interior/exterior general industrial metal coating applications
- Interior/exterior plastic components coating applications
- Interior/exterior wood coatings for floor, furniture, or millwork applications

Processing Aqueous binders tend to form serum - water will evaporate in the container and condensate on the surface. The products should therefore be homogenized before use. No coalescent agents are required in coatings based on Laromer® UA 8983 Aqua, allowing the manufacture of zero VOC coatings.

Laromer® UA 8983 Aqua can be mixed with other emulsions, however, the pH should be observed. Formulations based on Laromer® UA 8983 Aqua can be colored with aqueous pigment preparations such as Luconyl® or stir-in pigments such as Xfast®.

Coatings should be allowed to thoroughly dry before UV curing to warrant adequate mechanical and chemical resistances. The drying temperature depends on the substrate and the film thickness. For best results, UV curing should occur immediately after physical drying.

A suitable photoinitiator must be used to photocure Laromer® UA 8983 Aqua. The photoinitiator types include, for example, α -hydroxy ketone, benzophenone, acyl phosphine oxide, and blends thereof, for typical coating applications. Liquid photoinitiators can be incorporated directly; powder types should be pre-dissolved in a suitable organic solvent, such as ethylene glycol monobutylether (EB). The amount of photoinitiator varies between 1 – 3% based on the desired Laromer® LR 8983 as delivered.

Extra 0.2-1.0 % of acyl phosphine oxide types (MAPO, MAPO-Liquid and BAPO) of photoinitiators are recommended for film thicknesses of 50 g/cm² and above and for pigmented UV systems.

In UV curable coatings, the photoinitiators' volatility should be observed. No tack-free films will have formed after evaporation of the water. Preparations containing photoinitiators should be stored in UV-impermeable plastic containers.

Please contact the local BASF technical specialist for further details.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Laromer® UA 8983 Aqua.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Laromer is a registered trademark of BASF Group.

© BASF Corporation, 2017



Responsible Care®
Good Chemistry at Work

BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation
24710 W Eleven Mile Road
Southfield, MI 48034
ph: 1(800) 231-7868
fax: 1(800) 392-7429
Email: DispersionsPigmentsCC@basf.com
Email: edtech-info@basf.com
www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.
Av. Insurgentes Sur # 975
Col. Ciudad de los Deportes
C.P. 03710
Mexico, D.F.
Phone: (52-55) 5325-2756
Fax: (52-55) 5723-3011