

GLOBALPRENE 1487 Styrene-Butadiene block copolymer 苯乙烯-丁二烯嵌段共聚物

Features 特性 :		Typical Application 一般應用 :			
• Oil-extended radial block copolymer	油展星型嵌段共聚物	• Footwear compounding	鞋底加工		
• High strength and low viscosity	高強度及低黏度	• Plastic Modification	塑膠改質		
• Reprocess able	可回收再加工				
Typical Properties :		Test Method	Unit	Value	Range
一般性質		測試方法	單位	數值	範圍
SM Content 苯乙烯含量		ASTM D5775	%	55	53~57
Specific Gravity 比重		ASTM D792	g/cc	0.94	N/A
Volatile Matter 揮發份		ASTM D5668	%	0.25	≤0.5
Ash Content 灰份		ASTM D5667	%	0.2	<1.0
Oil content 油份		ASTM D5774	wt%	28.5	26 ~ 31
Melt Flow Index (190°C, 5kg) 熔融流動指數		ASTM D1238	g/10min	12	9 ~ 15
Hardness 硬度		ASTM D2240	shore A	92	90 ~ 94

Packing 包裝: 20 kg paper bag 20 公斤 紙袋

600 kg super bag 600 公斤 太空袋

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)

Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.
以上所列之各項資料為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

商業服務處

Sales Services

臺灣 臺北市松山區八德路四段 85 號 3 樓

3F., No.85, Sec. 4, Bade Rd., Songshan Dist., Taipei City 105, Taiwan

Tel : +886-2-27631611

Fax : +886-2-27482661

環球橡膠股份有限公司

LCY GRIT CORP.

臺灣 高雄市小港區中林路 16 號

No.16, Zhonglin Rd., Xiaogang Dist., Kaohsiung City 812, Taiwan

Tel : +886-7-8712268

Fax : +886-7-8712296

惠州李長榮橡膠有限公司

HUIZHOU LCY ELASTOMERS CORP.

中國 廣東省惠州市大亞灣經濟技術開發區石化區石化大道中 299 號

299 Shihua Dadaozhong, Dayawan Economic & Technological Development Zone, Huizhou, Guangdong, 516082, P.R.C.

Tel : +86-752-5599000

Fax : +86-752-5599002

LCY Elastomers LP

4803 Decker Drive, Baytown, Texas 77520, USA

Tel : +1-281-424-6100

Fax : +1-281-424-6340