

# OMICURE® BC-120

Latent Curing Agent, Accelerator  
Trichloro(N,N-Dimethyloctylamine)Boron  
CAS No. 34762-90-8

## DESCRIPTION

OMICURE® BC-120, a Lewis Acid, is intended for use as a room-temperature-latent elevated-temperature catalytic curing agent for epoxy resins. BC-120, in combination with liquid epoxies, produces clear homogeneous formulations. To incorporate BC-120, heat the resin to 30-35 °C and stir in the curing agent. When used to cure EPALLOY® 7190 (DGEBA), where 1 to 9 phr BC-120 are typically used, room temperature shelf lives of greater than one year can be realized. Curing can be accomplished at temperatures above 120 °C. Higher temperatures reduce cure times. When using 3 phr BC-120 with 7190, and curing for 2 hours at 150 °C, a Tg of 120 °C was obtained. Using higher amounts of BC-120 will shorten cure times and increase Tg (see Table 1). Higher Tgs can also be achieved by using epoxy novolac resins in place of 7190 (see Table 2).

BC-120 can also be used as an accelerator in the aromatic amine, acid anhydride or dicyandiamide cure of epoxy resins. The pot lives of these formulations will be significantly longer than those obtained when using BF3 MEA or DMP-30 as the accelerator. Typically 0.5 to 1.0 phr BC-120 are used for acceleration.

## APPLICATIONS

As a latent accelerator in the dicyandiamide cure of epoxy resins used in:

- Castings
- Potting
- Adhesives
- Electric enamels
- Filament winding
- Pultrusion

**TYPICAL  
PROPERTIES**

Appearance	Waxy solid to liquid
Color	Tan to brown
Melting Point, °C	25 - 35
Water Content, max %	0.1
pH	max 3
Solubility in EPALLOY 7190	Yes

**PERFORMANCE  
DATA**

**TABLE 1**  
Effect of OMICURE BC-120 Concentration, in EPALLOY 7190, on Tg

Fomulation, pbw	A	B	C	D	E	F	G
EPALLOY 7190	100	—————>					
OMICURE BC-120	1	3	5	6	7	8	9

Thermal Analysis Ramp Cure to 285 °C @ 20 °C/min.	A	B	C	D	E	F	G
Enthalpy, J/g	62	185	342	388	426	453	453
Onset, °C	-	131	132	135	132	133	133
Tg, °C	-	41	104	127	139	140	137

CONCLUSION: The recommended concentration of BC-120 to provide the highest Tg with EPALLOY 7190 is 7 to 8 phr.

**TABLE 2**  
Effect of OMICURE BC-120 Concentration, in EPALLOY 8250, on Tg

Fomulation, pbw	A	B	C	D	E
EPALLOY 8250	100	—————>			
OMICURE BC-120	5	6	7	8	9

Thermal Analysis Ramp Cure to 295 °C @ 20 °C/min.	A	B	C	D	E
enthalpy, J/g	363	414	460	464	465
onset, °C	129	128	128	130	129
Tg, °C	138	150	152	147	145



### PACKAGING & AVAILABILITY

OMICURE BC-120 is supplied in 5 gal plastic pails (45 lb. net) with a Reike pour spout.

### HEALTH & SAFETY PRECAUTIONS

**CAUTION:** OMICURE BC-120 is a highly acidic material. Avoid contact with skin or eyes as BC-120 may cause irritation and burning. Do not inhale vapors. Use with adequate ventilation. Wash exposed skin and contaminated clothing after handling.

OMICURE BC-120 should be stored in tightly closed, acid-resistant containers. Avoid exposure to humidity. If upon opening a container, BC-120 is found to be in its solid state, mild heating (about 100 °F) in a sealed container will remelt the product.

Refer to CVC Thermoset Specialties Material Safety Data Sheet on OMICURE BC-120 for additional safety and health information. The MSDS is revised as new data becomes available.

### DISCLAIMER

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions, and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. CVC Thermoset Specialties shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond CVC's direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner. IN NO EVENT SHALL SELLER BE LIABLE FOR ANY INCIDENTAL, CONSEQUENTIAL OR SPECIAL DAMAGES.

CVC Thermoset Specialties  
844 North Lenola Road / Moorestown, NJ 08057  
Phone: 856-533-3000 / Fax: 856-533-3003 / [www.cvcthermoset.com](http://www.cvcthermoset.com)



An Emerald Performance Materials® Company