

KaMin® HG90

Kaolin Clay - Ultrafine, high brightness

Product Description:

KaMin® HG90 is a high brightness, ultra-fine particle size, platy kaolin with moderate water demand providing good tinting strength, TiO2 extension and gloss in water based paints. KaMin® HG90 is ideally suited for water-borne paint and ink applications, where high brightness and whiteness are important.

Physical Form: Dry, Slurry

Type: Kaolin Clay - Ultrafine, high brightness

Typical Physical Properties

| Test | Value | Method |
|--|-----------|--------------------------|
| Brightness, % Reflectance (TAPPI) | 90-91.5 | ASTM E1164 |
| Moisture, 105°C, max, as produced, % | 1.5 | KAM-QA-WI-008 |
| Screen Residue, 325 Mesh, % | 0.005 | KAM-QA-WI-001 |
| pH, (100 g/250 ml H ₂ O) | 6-8 | KAM-QA-WI-010 |
| Average Stokes Equivalent Particle Diameter (mm) | 0.2 | KAM-QA-WI-009 |
| Median Particle Size (mm), (Malvern) | 0.4 | KAM-QA-WI-035 |
| Specific Gravity | 2.6 | ASTM C127 |
| Surface Area, BET, M2/g | 21 | ASTM D3363 |
| Oil Absorption g/100g | 42 | ASTM D3363 |
| Crystalline Silica (quartz), % | 0.10 | KaMin Proprietary Method |
| Bulk Density-Loose (Lbs/ft ²) | | KAM-QA-WI-002 |
| Bulk Density Tapped (Lbs/ft ²) | 50; 56 | KAM-QA-WI-002 |
| Shipping Point | Wrens, GA | |

CAS # 1332-58-7

The above data are representative data for this product and should not be perceived as specifications or maximum/minimum values.

The information contained herein is believed to be accurate and reliable, but KaMin LLC MAKES NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY OTHER EXPRESS OR IMPLIED WARRANTY. The information herein relates only to the specific product described and not to such product in combination with any other product. Providing information as herein contained is not to be regarded by implication or otherwise as conveying any rights or permission for use which would violate any patent rights, proprietary rights or violate any law, safety code or insurance regulation. Natural mineral products are subject to the normal variations related to the deposits from which they are mined.